



1537 E. McFADDEN AVE. SUITE A SANTA ANA, CA. 92705

Call 714-361-1435
or visit www.aspseal.com

GSG

To shop online
visit www.sealsales.com

NON ASBESTOS GASKET JOINTING SHEET

Description

Style GSG, General Service Gasketing, is a high quality general service sheet, made from Aramid fiber with mineral fiber & inorganic bonded with Synthetic NBR Elastomers. Recommended for use in sealing against oils, solvents, fuels, non-aggressive solutions, and service conditions up to 600°F. Available in thicknesses from 1/64" to 1/8"

- Aramid Fibers with NBR binder
- Excellent general service sheet
- Available in 60" x 60" sheets
- Available in thicknesses of 1/64", 1/32", 1/6", 3/32", and 1/8"

All information and recommendations contained in this specification sheet are to the best of our knowledge correct. Since conditions of use are beyond our control, users must satisfy themselves that the products are suitable for the intended processes and uses. No warranty is given or implied in respect of information or recommendations or that any use of the products will not infringe rights belonging to other parties. In any event or occurrence our liability is limited to our invoice value of the goods delivered by us to you.

We reserve the right to change product design and properties without notice.



PHYSICAL PROPERTIES

Color	Green
Density(lbs/cubic ft):	106-118lbs/ft ³
Maximum Service Temperature:	600°F (315°C)
Recommended Maximum Continuous Temperature:	400°F (204°C)
Maximum Service Pressure:	1422 psi
Compressibility (after 1hour at 210°F)-ASTM F36A:	7-15%
Recovery-ASTM F36A	40% min
Creep Relaxation-ASTM F38B	25% max
Thickness Increase (max%)-ASTM Oil #3):	12%
Weight Increase (max%)-ASTM F146-ASTM Oil Fuel B):	15%max
Thickness Increase (max%)- ASTM F146- (ASTM Oil Fuel B):	12% max

